

DESCRIPTION

ECO-RISE™ 3.0 (3S) is a two component, closed cell, rigid polyurethane system for pour foam applications. This foam is low viscosity and is specifically designed for pour operations to produce rigid foam for concrete slab and road jacking and stabilization. This product has excellent processing characteristics. Good dimensional stability and adhesion to substrate. **ECO-RISE™ (3S)** is formulated using only virgin Polyether polyols enhancing its hydrolytic stability characteristics.

FEATURES

- Liquid components can be shipped non-hazardous by OSHA Hazard Communication Standard (29 CFR 1910.1200).
- No dangerous heavy metal catalyst (such as lead or mercury).
- No ozone depleting products (ODP).
- No bromine or other halogenated components.
- No formaldehyde components.
- Mildew, bacteria, and fungus resistant.
- Contains renewable resource components.
- Considered safe for burial and landfill disposal.
- Compliant with USDA/FDA requirements for incidental food contact.

RECOMMENDED USES

- Molding
- Walk in coolers
- Where medium density, pour in place system is required.

CONTAINER SIZES

This product sold in standard 100 gallon drum and 500 gallon tote sets. Material containers are translucent, allowing applicators to view fluid levels. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

TYPICAL PHYSICAL PROPERTIES

Viscosity @ 77°F (25°C)	"A" 200 ± 50 cps "B" 700 ± 50 cps
Specific Gravity @ 25°	"A" 1.24 g/ml "B" 1.25 g/ml
Mixing ratio, % by weight	"A" 50 "B" 50
Color	"A" Amber "B" Light Yellow
Storage Temperature	60° - 90°F (15° - 32°C)
Shelf Life (unopened)	12 months
* When continuously stored and maintained at above temperatures	

REACTIVITY PROFILE @ 77°F (25°C)

Cream Time	3 sec.
Rise Time	6 sec.
Tack Free Time	6 sec.

The reactivity profile of the foam can be varied as needed. The samples for tests were poured with Gusmer 20/35 @ 1200 psi dynamic pressure. Primary and hose heat @ 125°F (52°C). Graco AP Fusion gun with AR 37/37 module with pour foam adaptor.

STORAGE & HANDLING

Maintain storage area for materials between 60 - 90°F at all times. Open drums with caution to prevent loss of blowing agent and potential personal chemical contamination.

PROCESSING EQUIPMENT

Standard 1:1 ratio, heated plural component equipment developing a minimum of 1200 psi (8.34 mpa) dynamic pressure with heating capabilities to 150°F (66°C) will adequately pour this product. These include Graco A-20, PMC PA-25, Gusmer FF-1600 or equivalent. Graco Air Purge Fusion, GX-7-400, Probler P2, or MP Fusion. Pre-heater temperature should be a minimum of 120° - 140°F (49° - 60°C).

Hose temperature should be 120° - 140°F (49° - 60°C). A hose thermometer inserted under the insulation near the gun should read a minimum of 110°F (43°C).

CAUTION: Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.

Substrate temperature should be a minimum of 50°F (10°C).

LIMITATIONS

This product is for professional use only.

Minimum material/container temperature for pour application is 70°F (21°C).

This product has not been tested for flame spread or smoke development.

Not to be installed within two inches (2") of heat emitting devices, where temperatures is in excess of two hundred degrees (200°F).

GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

WARNING: Contact with skin or inhalation of vapors may cause an allergic reaction. Causes eye damage/irritation. Avoid eye contact with liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and other exposed areas.

CONTAMINATION: Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, carbon dioxide created pressure can develop. Do not attempt to use contaminated material.

EYE PROTECTION: Safety eye wear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid

splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

SKIN PROTECTION: Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

RESPIRATORY PROTECTION: Respiratory protection is **MANDATORY!** The vapors must not exceed the TLV (0.02 parts per million). Harmful if inhaled and may cause allergy or asthma symptoms. Use a respirator approved for isocyanates and organic vapors. If you are not sure, or not able to monitor levels, or if you are spraying in an enclosed/ indoor area, use MSHA/NIOSH approved supplied air respirator. Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

INGESTION: Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.

FIRE HAZARD: Fires involving "A" or "B" components may be extinguished with carbon dioxide, dry chemical, or inert gas. Application of large quantities of water spray is recommended for spill fires. Personnel fighting the fire must be equipped with NIOSH approved self contained breathing apparatus.

Cleaning of Spills or Leakage

Cover the area with an inert absorbent material such as clay or vermiculite and transfer to metal waste containers. Saturate with water but do not seal the container with the isocyanates and water mixture. The area should then be flushed with large amounts of water, in the case of the "B" component, or 5% aqueous ammonia, in the case of the "A" component. Dispose of these materials in compliance with federal, state and local regulations.

Caution: Isocyanates will react with water and generate carbon dioxide. This could result in rupture of closed containers.

WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. **SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY**

OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.



SEAMLESS SOLUTIONS FOR OVER 40 YEARS

SPI The Single Source Solution Since 1974
Serving the Plural-Component Industry

Product & Equipment Technical Assistance
24 hours - 7 days a week 800 627 0773

CONTACT US

2410 104th St. C. S. Suite D, Lakewood, WA 98499

WWW.SPECIALTY-PRODUCTS.COM

1 800 627 0773 FAX 253 588 7196

info@specialty-products.com



**"Proudly Manufactured
in the USA"**