

DESCRIPTION

HM-VK™ is an ultra high-strength, handmix polyurea elastomeric adhesive with extended pot life.

FEATURES

- 100% solids, no solvents, and zero VOCs.
- Pot mixed.
- Compliant with FDA/USDA for incidental food contact.
- Liquid components can be shipped non-hazardous by the OSHA Hazard Communication Standard (29 CFR 1910.1200).

RECOMMENDED USES

- High strength polyurea adhesive.

COLORS

HM-VK™ is available in SPI standard Neutral (honey) color.
Note: In continuous full-light exposure, HM-VK™ will yellow over a period of time.

PACKAGING

HM-VK™ is sold in 1 quart, 1 gallon, 5 gallon, and 55 gallon kits.

CURING SCHEDULE

Gel	26 ± 2 min
Tack Free	30 ± 2 min
Post Cure**	12 hour
Recoat	12 hours
Above curing schedule is based on 125 g @ 77°F (25°C). Variables that will change the speed of reaction and length of pot life:	
<ul style="list-style-type: none"> • Weight of product used • Starting temperature of test product • Air temperature • Substrate temperature 	

**Complete polymerization to achieve final strength can take up to several days, depending on a variety of conditions or substrate type.

DRY PROPERTIES*

Hand Mix	
Tensile Strength ASTM D 638	± 6,671 psi (46 mpa) avg
Elongation ASTM D638	± 506%
Hardness (Shore A) ASTM D2240	95 ± 5
Hardness (Shore D) ASTM D2240-81	44 ± 5
Modulus 300% ASTM D412	1395 psi (9.7 mpa)
Service Temperature	-30° - +250°F (-34° - +121°C)

*All cured film properties are approximate since processing parameter, ad-mixture types, and quantities change physical properties of the cured elastomer.

All samples for above tests were force cured 48 hours or aged for more than three weeks. It is recommended that the user perform their own independent testing.

WET PROPERTIES

Solids by Volume	100%
Solids by Weight	100%
Volatile Organic Compounds	0 lbs./gal (0 g/l)
Theoretical Coverage DFT	100 sq. ft. @ 16 mils/gal
Weight per gallon (approx.)	8.8 lbs. (4.0 kg)
Number of coats	1 or more
Mix Ratio (by volume)	1 "A" : 4 "B"
Viscosity (cPs) @77°F (25°C)	A: 20 - 60 cPs B: 2500 - 3500 cPs
Shelf Life Unopened Containers @ 60 - 90°F (15 - 32°C)	Six Months

Minimum material/container temperature for application is 75°F (24°C).

GENERAL APPLICATION INSTRUCTIONS

Apply HM-VK™ to only clean, dry, sound surfaces free of loose particles or other foreign matter.

HM-VK™ “A” containers are clearly marked indicating what size “B” container is required for the 4:1 ratio mix by weight.

HM-VK™ should remain sealed while not in use as exposure to the atmosphere will reduce physical properties of end product.

After introducing the “A” side to the “B” side the mixture should be folded in with a stir stick and in an even manner, scraping the sides and bottom of container as you mix. DO NOT whip or mix with an electric mixer. Once mixed drizzle onto prepared substrate in an overlapping figure 8 pattern to allow for even distribution to spread with a notched type trowel or preferred tool. Note: porous substrates will likely create “out gas” bubbles. Heating the substrate may help mitigate this.

Read and observe all precautions, instructions, and limitations that are included with all containers of HM-VK™.

LIMITATIONS

This product is for professional use only.

This product must be stored at temperatures between 70° - 90°F (21° - 30°C). Storing this product at temperatures below 70°F (21°C) will cause the polymer to become very viscous.

HM-VK™ is best processed at 80°F (27°C) ± 5.

Processing HM-VK™ below 75°F will cause the polymer to become very viscous and negatively impact the ability to get a good mix.

Processing HM-VK™ at temperatures above 80°F (27°C) will speed up the reaction and shorten pot life. Pot life is approximately 24 - 28 minutes at 77°F (25°C).

Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, CO₂ created pressure can develop. Do not attempt to use contaminated material.

Note: The material supplied is a two component system (Component “A”/Component “B”) which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components.

GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

WARNING: Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact with the liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and exposed areas.

CLEAN UP: Use DPM, NMP, and Polyclean.

EYE PROTECTION: Safety eye wear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

SKIN PROTECTION: Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

RESPIRATORY PROTECTION: Harmful if inhaled and may cause allergy or asthma symptoms. Use a respirator approved for isocyanates and organic vapors. If you are not sure, or not able to monitor levels, or if you are spraying in an enclosed/indoor area, use MSHA/NIOSH approved supplied air respirator. Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

INGESTION: Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.



SEAMLESS SOLUTIONS FOR OVER 40 YEARS



WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof

SPI The Single Source Solution Since 1974
Serving the Plural-Component Industry

Product & Equipment Technical Assistance
24 hours - 7 days a week 800 627 0773



SPI Website

CONTACT US

2410 104th St. C. S. Suite D, Lakewood, WA 98499
WWW.SPECIALTY-PRODUCTS.COM
1 800 627 0773 FAX 253 588 7196
info@specialty-products.com



SPI Media



"Proudly Manufactured in the USA"