

## DESCRIPTION

**POLYSHIELD HT™ SL is a fast-set, high-performance, spray-applied, plural-component, pure polyurea elastomer. This system is based on amine-terminated polyether resins, amine chain extenders and prepolymers. It provides a flexible, tough, resilient monolithic membrane with good water and chemical resistance.**

## FEATURES

- 100% solids, no solvents, and zero VOC's.
- Fast-set: handle in two minutes or less.
- Hydrophobic, and therefore affected very little by damp, cool surfaces during application.
- High dry temperature stability with a dry working temperature up to 250°F (121°C) with intermittent temperatures up to 300°F (148°C).
- High abrasion resistance.
- High elongation for crack bridging.
- Excellent encapsulation characteristics.
- Compliant with FDA/USDA for incidental food contact.

## RECOMMENDED USES

- Coating for steel or other substrate exposed to corrosion.
- Liner for concrete tanks, concrete floors, ponds, lagoons, reservoirs, dikes, tunnels, barges, etc.
- Replace or repair failed existing sheet membrane liners.
- Protective elastomer for sprayed-in-place urethane foam.
- Steel tanks, silos, and pipes.
- Rock shield for pipelines.
- Planter box liner.
- Plywood decks.
- Bridge deck waterproofing.
- Encapsulation for EPS or other types of flotation materials.
- Encapsulation for asbestos, lead paint, or other dry hazardous materials (Consult SPI).
- Earthen containment used with or without geotextile.
- Concrete parking decks.
- Wood deck coating.
- Courtyard membrane.
- Plywood walkways.

## TYPICAL PHYSICAL PROPERTIES\*

| @34 mils (0.8 mm)                           |                                  |
|---|----------------------------------|
| <b>Tensile Strength<br/>ASTM D638</b>       | ± 4,400 psi (30 mpa)             |
| <b>Elongation<br/>ASTM D638</b>             | ± 400%                           |
| <b>Hardness (Shore A)<br/>ASTM D2240-81</b> | 95 ± 5                           |
| <b>Hardness (Shore D)<br/>ASTM D2240-81</b> | 45 ± 5                           |
| <b>100% Modulus<br/>ASTM D412</b>           | 1,450 psi (10 mpa) ± 5%          |
| <b>300% Modulus<br/>ASTM D412</b>           | 2,989 psi (21 mpa) ± 5%          |
| <b>Tear Resistance<br/>ASTM D624</b>        | 430 PLI (107 KN/m)               |
| <b>** Exposure Temperature</b>              | -60° - +250°F<br>(-50° - +121°C) |

\*All cured film properties are approximate since processing parameters, admixture types, and quantities change physical properties of the cured elastomer. All samples for above tests were force cured 48 hours or aged for more than three weeks. It is recommended that the user perform their own independent testing.

\*\* Test performed in a dry, static environment.

## CURING SCHEDULE

|                    |              |
|--------------------|--------------|
| <b>Gel</b>         | ± 8 sec.     |
| <b>Tack Free</b>   | ± 12 sec.    |
| <b>Post Cure**</b> | 24 hour      |
| <b>Recoat</b>      | 0 - 12 hours |

\*\*Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type. The samples for tests were sprayed with Graco HXP3 @ 3,200 psi dynamic pressure (22 mpa). Primaries/Hose Heat 170°F (77°C) Graco MP Fusion Gun with 29/29 mixing chamber with 040 ceramtip.

## INDUSTRIES

- **Infrastructure** - Water, Transportation, Commercial & Industrial, Rehab/Retrofitting Communications.
- **Energy** - Oil & Gas, The Electric Grid, Nuclear, Wind, Hydro-Electric (Turbine).
- **Engineering** - OEM, Custom Product Formulations, Toll Blending, Bedliners & Equipment Coatings, Defense.
- **Environmental** - Groundwater Protection, Waste Encapsulation, Soil Stabilization, Pipe/Tank Decommissioning, Coal/Mining.

## TEST INFORMATION

|  |            |            |
|--|------------|------------|
| <b>ABRASION RESISTANCE<br/>ASTM D4060<br/>1000 g - 1000 cycles</b> | H-18 wheel | 92 mg loss |
|  | CS-17      | 6 mg loss  |

## WET PROPERTIES

|   |                                     |
|---|-------------------------------------|
| <b>Solids by Volume</b>   | 100%                                |
| <b>Solids by Weight</b>   | 100%                                |
| <b>Volatile Organic Compounds</b>                                 | 0 lbs/gal (0 g/l)                   |
| <b>Theoretical Coverage DFT</b>                                   | 100 sq. ft. @ 16 mils/gal           |
| <b>Weight per gallon (approx)</b>                                 | 8.8 lbs. (4.0 kg)                   |
| <b>Number of coats</b>  | 1 - 2                               |
| <b>Mix Ratio</b>  | 1 "A" : 1 "B"                       |
| <b>Viscosity (cps)</b>  | A: 600 ± 100 cPs<br>B: 325 ± 25 cPs |
| <b>Shelf Life Unopened Containers<br/>@ 60 - 90°F (15 - 32°C)</b> | Six Months                          |

Minimum material/container temperature for application is 70°F (21°C).

## COLORS

POLYSHIELD HT™ SL is available in SPI standard colors (Sand, Medium Grey, and Black). Custom colors available upon request. Note: POLYSHIELD HT™ SL is an aromatic polyurea. Therefore, with all aromatics, color change and superficial oxidation will occur. Aliphatic urethane, polyaspartics, and other suitable topcoats can be used where long-term color stability and increased longevity in full sun exposure are of critical importance.

## PACKAGING

This product sold in standard 110 gallon drum and 550 gallon tote sets. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

## GENERAL APPLICATION INSTRUCTIONS

Apply POLYSHIELD HT™ SL only to clean, dry, sound surfaces free of loose particles or other foreign matter. POLYSHIELD HT™ SL can be sprayed over a broad range of ambient and substrate temperatures. It is recommended that POLYSHIELD HT™ SL be sprayed in multi-directional (north/south-east-west) passes to ensure uniform thickness.

Contact SPI technical service personnel for specific surface preparation for your application.

### COMMON SUBSTRATES:

**STEEL:** 2-5 mil anchor profile is best for maximum adhesion and varies per application and conditions; adhere to proper SSPC standards.

**NON-FERROUS METALS:** (minimum recommended surface preparation) Prepare surface in accordance to SSPC-SP16 (Brush-off Blast Cleaning of Non-Ferrous Metals)

**WOOD:** Clean, dry and sanded for a smooth (to remove burs, splinters, loose debris) surface in which to apply polyurea onto. (It is recommended to prime wood and other porous surfaces before application of heated, fast-set polyureas to reduce pin holing)

**CONCRETE:** (minimum recommended surface preparation) Prepare concrete in accordance with SPI Concrete Prep Guide and SSPC/NACE Standards.

**PREVIOUSLY APPLIED COATINGS:** SPI recommends UB™ (ULTRA BOND™) products over existing coatings that are past the recoat window and/or application over other coatings. The use of SPI Prep Wipe™ solution will tack up the existing polyurea coating and can help promote bonding of the POLYSHIELD HT™ SL. Contact SPI for additional information. Contact SPI for additional information.

On all above listed substrates and others, please contact SPI Sales or Technical Support for more information specific to your application, including industry standards such as SSPC and NACE. Adhesion tests are always recommended prior to application.

## MIXING & THINNING

Thoroughly agitate the "B" components of this product prior to application. Use a SPI folding blade mixer, or equivalent equipment approved by SPI. Install mixer through the extra 2" bung hole provided on all "B" drums. Care must be taken not to cross contaminate the individual components with the mixing equipment. Thinning is not required. Using any thinner may adversely affect product performance.

## PROCESSING EQUIPMENT & SETTINGS

### MACHINES:

|                                       |  |  |
|---------------------------------------|--|--|
| <b>GRACO</b><br>(Gusmer, Glass-craft) | <ul style="list-style-type: none"> <li>Reactor HXP2</li> <li>Reactor HXP3</li> <li>H25</li> <li>20/35</li> </ul> | <ul style="list-style-type: none"> <li>20/35 Pro</li> <li>H3500</li> <li>HV-20/35</li> </ul> |
| <b>PMC</b>                            | <ul style="list-style-type: none"> <li>*PH-25</li> <li>*PH-40</li> </ul>   | <ul style="list-style-type: none"> <li>PHX-2</li> <li>PHX-25</li> <li>PHX-40</li> </ul>      |
| <b>SPRAY FOAM EQUIP &amp; MFG</b>     | <ul style="list-style-type: none"> <li>*5/12K</li> <li>*6/6K</li> </ul>  | <ul style="list-style-type: none"> <li>6/12K</li> </ul>                                      |
| *2,000 psi machines                   |  |  |

### GUNS:

|                                       |   |  |
|---------------------------------------|---|--|
| <b>GRACO</b><br>(Gusmer, Glass-craft) | <ul style="list-style-type: none"> <li>Fusion MP</li> <li>Fusion AP</li> <li>GAP Pro</li> <li>GX7-DI</li> </ul> | <ul style="list-style-type: none"> <li>GX-8 Pro</li> <li>P2</li> <li>P2 Elite</li> <li>P2 Elite "C"</li> </ul> |
| <b>SPRAY FOAM EQUIP &amp; MFG</b>     | <ul style="list-style-type: none"> <li>Boss</li> </ul>  |  |

- Standard 1:1 ratio, heated, plural-component equipment developing a minimum of 1500 psi (10 mpa) dynamic pressure with heating capabilities to 175°F (79°C) will adequately spray POLYSHIELD HT™ SL.
- Primary heater temperature should be at 160-170°F (71-76°C).
- Hose temperature should be at 160-170°F (71-77°C). A hose thermometer inserted under the insulation near the gun should read a minimum of 145-155°F (63-68°C).
- Physical properties will be enhanced when sprayed at higher pressure (3000 psi or more), utilizing an impingement mix gun such as MP Fusion or GX7-DI gun.

If you own a machine that is not listed above please contact your SPI representative for information and instructions.

## PARAMETERS & LIMITATIONS

- POLYSHIELD HT™ SL is for professional use only.
- POLYSHIELD HT™ SL must be stored at temperatures between 60—90°F (15—30°C).
- Liquid temperature in drums during application 70—100°F (21—38°C).
- Apply POLYSHIELD HT™ SL when surface and air temperatures are above 40°F (5°C) and the surface temperature is at least 5°F (3°C) above dew point and rising.
- Minimum material/container temperature for spray application is 70°F (21°C).
- Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected. CO<sub>2</sub> created pressure can develop. Do not attempt to use contaminated material.
- Undried air exposed to liquid components will reduce

physical properties of the cured coating.

Note: The material supplied is a two component system (component "A"/component "B", which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components by the person applying the polymers.

## GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300 INT'L 1-703-527-3887.**

**WARNING:** Contact with skin or inhalation of vapors may cause an allergic reaction. Causes eye damage/irritation. Avoid eye contact with liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and other exposed areas.

**CONTAMINATION:** Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, carbon dioxide created pressure can develop. Do not attempt to use contaminated material.

**EYE PROTECTION:** Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

**SKIN PROTECTION:** Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

**RESPIRATORY PROTECTION:** Harmful if inhaled and may cause allergy or asthma symptoms. Use a respirator approved for isocyanates and organic vapors. If you are not sure, or not able to monitor levels, or if you are spraying in an enclosed/indoor area, use MSHA/NIOSH approved supplied air respirator. Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

**INGESTION:** Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.



SEAMLESS SOLUTIONS FOR OVER 40 YEARS



### WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof

**SPI The Single Source Solution Since 1974**  
**Serving the Plural-Component Industry**

**Product & Equipment Technical Assistance**  
**24 hours - 7 days a week 800 627 0773**



SPI Website

### CONTACT US

2410 104<sup>th</sup> St. C. S. Suite D, Lakewood, WA 98499  
[WWW.SPECIALTY-PRODUCTS.COM](http://WWW.SPECIALTY-PRODUCTS.COM)  
1 800 627 0773 FAX 253 588 7196  
[info@specialty-products.com](mailto:info@specialty-products.com)



SPI Media



**"Proudly Manufactured in the USA"**