

## DESCRIPTION

**HARD CAP™ 100 spray-applied, plural-component, 100% pure polyurea is an ideal choice when a durable high build coating for interior and exterior applications with excellent color stability and gloss retention is required. HARD CAP™ 100 provides a flexible, resilient, tough, monolithic membrane with good water and chemical resistance.**

## FEATURES

- 100% solids, no solvents, and zero VOCs.
- Extended tack time to allow deep surface penetration as well as a smooth, uniform finish.
- High dry temperature stability with a dry working temperature up to 200°F (93°C).
- Compliant with FDA/USDA for incidental food contact.
- HARD CAP™ 100 can be applied by several methods. These include, heated plural-spray, in line static mix spray, external static mix pour, or brushed.
- HARD CAP™ 100 is available with and adhesion enhancing ad-mixture for additional adhesion to inorganic surfaces such as glass, ferrous metals, concrete, etc. Contact a SPI technical service person for specifics.
- HARD CAP™ 100 is also available with a microbial resistant additive to minimize mold/mildew growth.

## RECOMMENDED USES

- A hard washable coating for floors, walls, ceiling, etc. in food and beverage processing facilities.
- For institutional applications such as clean rooms, hospitals, etc. where an easily cleanable seamless surface is required.
- Fountains, reflection pools, and aquariums.
- Stop erosion on concrete, brick or stone while retaining its natural look.
- Apply to metal or concrete structures such as bridges and towers, to facilitate visual inspection for structural integrity.
- Preserve archaeological artifacts.

## COLORS

HARD CAP™ 100 is available in White and Clear. Custom colors available upon request.

## DRY PROPERTIES\*

| @ 60 mils (1.52 mm)                                |                                |
|--|--------------------------------|
| <b>Tensile Strength<br/>ASTM D 638</b>             | ± 2,300 psi (16 mPa)           |
| <b>Elongation<br/>ASTM D638</b>                    | ± 68%                          |
| <b>Hardness (Shore A)<br/>ASTM D2240</b>           | 98 ± 5                         |
| <b>Hardness (Shore D)<br/>ASTM D2240</b>           | 65 ± 5                         |
| <b>Moisture Vapor Transmission<br/>ASTM E96-80</b> | 0.018                          |
| <b>Tear Resistance<br/>ASTM D624</b>               | 519 PLI (91 KN/m)              |
| <b>Service Temperature</b>                         | -30° - +200°F<br>(-1° - +93°C) |

\*All cured film properties are approximate since processing parameter, ad-mixture types, and quantities change physical properties of the cured elastomer.

All samples for above tests were force cured 48 hours or aged for more than three weeks. It is recommended that the user perform their own independent testing.

## PACKAGING

This product sold in standard 110 gallon drum and 550 gallon tote sets. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

## CURING SCHEDULE

|                    |                   |
|--------------------|-------------------|
| <b>Gel</b>         | 1:35 min          |
| <b>Tack Free</b>   | 45 min            |
| <b>Post Cure**</b> | 24 hour           |
| <b>Recoat</b>      | 30 min - 12 hours |

\*\*Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type.

The samples for tests were sprayed with SPI Gusmer 18/18 @ 1300 psi dynamic (9 mpa). Primaries/Hose Heat 160°F (71°C,) D-7 gun with 46 mixing chamber. Test results from Huntsman Corporation.

## WET PROPERTIES

|   |  |
|---|--|
| <b>Solids by Volume</b>                                       | 100%                                     |
| <b>Solids by Weight</b>                                       | 100%                                     |
| <b>Volatile Organic Compounds</b>                             | 0 lbs./gal (0 g/l)                       |
| <b>Theoretical Coverage DFT</b>                               | 100 sq. ft. @ 16 mils/gal                |
| <b>Weight per gallon (approx.)</b>                            | 8.8 lbs. (4 kg)                          |
| <b>Number of coats</b>  | 1 or more                                |
| <b>Mix Ratio</b>  | 1 "A" : 1 "B"                            |
| <b>Viscosity @77°F (25°C)</b>                                 | A: 1000 ± 100 mPa.s<br>B: 500 ± 100 mPa. |
| <b>Shelf Life Unopened Containers @ 60 - 90°F (15 - 32°C)</b> | 6 Months                                 |

Minimum material/container temperature for application is 70°F (21°C).

## MIXING & THINNING

Thoroughly agitate the "B" components of this product prior to application. Use a SPI folding blade mixer or equivalent equipment approved by SPI. Install mixer through the extra air specific 2" bung hole provided on all "B" drums. Care must be taken not to cross contaminate the individual components with the mixing equipment; for best mixing results, supply the SPI mixer with 25 cfm of air at 100 psi. Thinning is not required. Using any thinner may adversely affect product performance.

## GENERAL APPLICATION INSTRUCTIONS

Apply HARD CAP™ 100 to only clean, dry, sound surfaces free of loose particles or other foreign matter. HARD CAP™ 100 can be sprayed over a broad range of ambient temperatures. Consult technical service for specific recommendations. It is recommended that HARD CAP™ 100 be sprayed in multi-directional (north-south/east-west) passes to ensure uniform thickness. The polyol "B" component must be thoroughly power mixed each day, prior to use. Consult technical service for specific primer, temperature and mixing equipment recommendations.

## PROCESSING EQUIPMENT & SETTINGS

### MACHINES:

|                                    |  |  |
|------------------------------------|--|--|
| <b>GRACO (Gusmer, Glass-craft)</b> | <ul style="list-style-type: none"> <li>H-XP2</li> <li>Reactor2 H-XP2</li> <li>H-XP3</li> <li>Reactor2 H-XP3</li> <li>*H25</li> <li>*Reactor2 H-30</li> <li>*H-40</li> <li>*Reactor2 H-40</li> <li>*H-50</li> <li>*Reactor2 H-50</li> <li>20/35</li> <li>20/35 Pro</li> </ul> | <ul style="list-style-type: none"> <li>*E-XP1</li> <li>E-XP2</li> <li>Reactor2 E-XP2</li> <li>E-XP2i</li> <li>*E-30</li> <li>*E-30i</li> <li>*Reactor2 E-30</li> <li>*E-10hp</li> <li>A-XP1</li> <li>*A-25</li> <li>H3500</li> <li>HV 20/35</li> </ul> |
| <b>PMC</b>                         | <ul style="list-style-type: none"> <li>PAX-25</li> <li>*PMCA-20</li> <li>*PA-25</li> <li>*PH-2</li> <li>*PH-25</li> </ul>  | <ul style="list-style-type: none"> <li>*PH-40</li> <li>PHX-2</li> <li>PHX-25</li> <li>PHX-40</li> </ul>  |
| <b>SPRAY FOAM EQUIP &amp; MFG</b>  | <ul style="list-style-type: none"> <li>*5/12K</li> <li>*6/6K</li> </ul>  | <ul style="list-style-type: none"> <li>6/12K</li> </ul>  |
| *2,000 psi machines                |  |  |

### GUNS:

|                                    |  |  |
|------------------------------------|--|--|
| <b>GRACO (Gusmer, Glass-craft)</b> | <ul style="list-style-type: none"> <li>Fusion MP</li> <li>GAP Pro</li> <li>GX7-DI</li> <li>GX-8 Pro</li> </ul> | <ul style="list-style-type: none"> <li>GX7-400</li> <li>P2</li> <li>P2 Elite</li> <li>P2 Elite "C"</li> <li>D-7</li> </ul> |
| <b>PMC</b>                         | <ul style="list-style-type: none"> <li>AP-2</li> </ul>   |  |
| <b>SPRAY FOAM EQUIP &amp; MFG</b>  | <ul style="list-style-type: none"> <li>Boss AP</li> </ul>  |  |

- Standard 1:1 ratio, heated, plural-component equipment developing a minimum of 2500 psi (10 mpa) dynamic pressure with heating capabilities to 170°F (77°C) will adequately spray HARD CAP™ 100.
- Machines capable of producing a higher dynamic psi may be required depending on the service environment the HARD CAP™ 100 will be exposed to. Consult SPI technical service personnel for additional information.
- Primary heater temperature should be at 160-170°F (71-77°C).
- Hose temperature should be at 160-170°F (71-77°C). A hose thermometer inserted under the insulation near the gun should read a minimum of 145-155°F (63-68°C).
- Physical properties will be enhanced when sprayed at higher pressure (3000 psi or more), utilizing an impingement mix gun such as MP Fusion or GX7-DI gun.

If you own a machine that is not listed above please contact your SPI representative for information and instructions.

## LIMITATIONS

HARD CAP™ 100 is for professional use only.

HARD CAP™ 100 must be stored at temperatures between 60° - 90°F (15° - 32°C).

Apply HARD CAP™ 100 when surface and air temperatures are above 40°F (5°C) and the surface temperature is at least 5°F (3°C) above dew point and rising.

Liquid temperature in containers/drums during application 70° F (21 °C) – 100°F (38°C).

Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, CO<sub>2</sub> created pressure can develop. Do not attempt to use contaminated material.

Note: The material supplied is a two component system (Component "A"/Component "B") which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components.

For the most up to date technical data sheet and/or safety data sheet visit our website at [www.specialty-products.com](http://www.specialty-products.com).

## GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300 INT'L 1-703-527-3887.**

**WARNING:** Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact with the liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and exposed areas.

**CLEAN UP:** Use DPM or NMP.

**EYE PROTECTION:** Safety eye wear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

**SKIN PROTECTION:** Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves complying with applicable health and safety standards shall be worn when handling this product. Cover as much of the exposed skin area as possible with appropriate clothing. Refer to safety data sheet (SDS).

**RESPIRATORY PROTECTION:** Harmful if inhaled and may cause allergy or asthma symptoms. Ensure adequate ventilation. If the respirator is the sole means of protection, use a full-face supplied respirator. Use respirators and components tested and approved under appropriate government standards such

as OSHA 29CFR 1910.134, NIOSH (US), or CEN (EU). Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

**INGESTION:** Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.



SEAMLESS SOLUTIONS FOR OVER 40 YEARS



### WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.

**SPI The Single Source Solution Since 1974**  
**Serving the Plural-Component Industry**

**Product & Equipment Technical Assistance**  
**24 hours - 7 days a week 800 627 0773**



SPI Website

### CONTACT US

2410 104<sup>th</sup> St. Ct. S. Ste D, Lakewood, WA 98499  
**SPECIALTY-PRODUCTS.COM**  
1 800 627 0773 FAX 253 588 7196  
info@specialty-products.com



SPI Media



**"Proudly Manufactured in the USA"**